

PPS SL
TECHNICAL DATA SHEET

FULL NAME: POLYPHENYLENE SULFIDE FILLED SOLID LUBRICANT

MECHANICAL PROPERTIES			
MODULUS OF ELASTICITY (TENSILE TEST) ¹⁾	DIN EN ISO 527-2	MPA	4600
TENSILE STRENGTH	DIN EN ISO 527-2	MPA	53
TENSILE STRENGTH AT YIELD	DIN EN ISO 527-2	MPA	53
ELONGATION AT YIELD 50MM/MIN	DIN EN ISO 527-2	%	2
ELONGATION AT BREAK 50MM/MIN	DIN EN ISO 527-2	%	2
FLEXURAL STRENGTH 2MM/MIN, 10 N ²⁾	DIN EN ISO 178	MPA	91
MODULUS OF ELASTICITY (FLEXURAL TEST) 2 MM/MIN, 10 N	DIN EN ISO 178	MPA	4800
COMPRESSION STRENGTH 1% - 2% - 5% 5MM/MIN, 10 N ³⁾	EN ISO 604	MPA	19/36/89
COMPRESSION MODULUS 5MM/MIN, 10 N ⁴⁾	EN ISO 604	MPA	3300
IMPACT STRENGTH (CHARPY) MAX. 7,5 ⁵⁾	DIN EN ISO 179-1EU	KJ/M ²	14
BALL INDENTATION HARDNESS ⁶⁾	ISO 2039-1	MPA	238

THERMAL PROPERTIES			
GLASS TRANSITION TEMPERATURE ⁷⁾	DIN EN ISO 11357	°C	94
MELTING TEMPERATURE	DIN EN ISO 11357	°C	281
SERVICE TEMPERATURE SHORT TERM ⁸⁾		°C	260
SERVICE TEMPERATURE LONG TERM		°C	230
THERMAL EXPANSION (CLTE) 23-60° C – LONG.	DIN EN ISO 11359-1;2	10 ⁻⁵ K ⁻¹	5
THERMAL EXPANSION (CLTE) 23-100° C – LONG.	DIN EN ISO 11359-1;2	10 ⁻⁵ K ⁻¹	6
THERMAL EXPANSION (CLTE) 100-150° C – LONG.	DIN EN ISO 11359-1;2	10 ⁻⁵ K ⁻¹	13
SPECIFIC HEAT	ISO 22007-4:2008	J/(G*K)	0.9
THERMAL CONDUCTIVITY	ISO 22007-4:2008	W/(K*M)	0.58

ELECTRICAL PROPERTIES			
SURFACE RESISTIVITY – SILVER ELECTRODE, 23°C, 12% R.H.	DIN EN 61340-2-3	Ω	10 ⁴ - 10 ¹⁰

D.H. LAMINA S.R.L.

Via Santellone, 29/A • 25080 Molinetto di Mazzano (BS) • Italy
Tel. +39 (0) 30 21 20 448 • Fax +39 (0) 26 20 813
Capitale Sociale € 46.800,00 Interamente versato
C.F. e Nr. Iscr. Registro Imprese 01685670174
P.I. IT01685670174 • REA BS-262362
PEC: dhlamina@pec.it • dhlamina@dhlamina.it • www.dhlamina.it

PPS SL
TECHNICAL DATA SHEET

VOLUME RESISTIVITY - SILVER ELECTRODE, 23°C, 12% R.H.	DIN EN 61340-2-3	Ω^*CM	$10^7 - 10^{12}$
---	------------------	--------------	------------------

MISCELLANEOUS PROPERTIES	TEST METHOD	UNIT	GUIDELINE VALUES
WATER ABSORPTION 24H / 96H (23°C) ⁹⁾	DIN EN ISO 62	%	<0.01 / < 0.01
RESISTANCE TO HOT WATER / BASES ¹⁰⁾	-	-	+
RESISTANCE TO WEATHERING ¹¹⁾	-	-	(+)
FLAMMABILITY (UL94) ¹²⁾	DIN IEC 60695-11-10	-	V0

REV.	DATE	DESCRIPTION	MODIFIED PARAGRAPHS	WRITTEN BY	APPROVED BY
01	12/2020	LAYOUT UPDATE	//	602.271	601.271

THIS DATASHEET AND ALL PROPRIETIES INDICATED COME DIRECTLY FROM THE PRODUCER'S STUDIES AND TESTS. D.H. LAMINA S.R.L. DOES NOT PRODUCE THE MATERIAL.
 THE CONTENTS OF THIS DATASHEETS ARE MEANT TO GIVE AN OVERVIEW OF THE PRODUCT'S PROPRIETIES. IT REFLECTS OUR CURRENT KNOWLEDGE AND MAY NOT BE COMPLETE. THE VALUES SHOULD BE TAKEN AS GUIDE VALUES BECAUSE THEY ARE DEPENDENT ON SURROUNDING CONDITIONS AND MACHINING METHODS. THE VALUES ARE IN NO WAY A LEGALLY BINDING ASSURANCE OF THE PRODUCT'S PROPRIETIES OR ITS SUITABILITY FOR USE IN A SPECIFIC APPLICATION. ALL STATED VALUES ARE AVERAGE ESTABLISHED FROM MANY INDIVIDUAL TESTS. FOR SPECIFIC APPLICATIONS, WE RECOMMEND DETERMINING SUITABILITY BY MEANS A TRIAL.

- (1) FOR TENSILE TEST: SPECIMEN TYPE 1B
- (2) FOR FLEXURAL TEST: SUPPORT SPAN 64MM, NORM SPECIMEN.
- (3) SPECIMEN 10x10x10MM
- (4) SPECIMEN 10x10x50MM, MODULUS RANGE BETWEEN 0.5 AND 1% COMPRESSION.
- (5) FOR CHARPY TEST: SUPPORT SPAN 64MM, NORM SPECIMEN.
- (6) SPECIMEN IN 4MM THICKNESS
- (7) FOUND IN PUBLIC SOURCES.
- (8) FOUND IN PUBLIC SOURCES. INDIVIDUAL TESTING REGARDING APPLICATION CONDITIONS IS MANDATORY.
- (9) Ø CA. 50MM, H=13MM
- (10) + GOOD RESISTANCE
- (11) (+) LIMITED RESISTANCE
- (12) CORRESPONDING MEANS NO LISTING AT UL (YELLOW CARD). THE INFORMATION MIGHT BE TAKEN FROM RESIN, STOCK SHAPE OR ESTIMATION. INDIVIDUAL TESTING REGARDING APPLICATION CONDITIONS IS MANDATORY.

D.H. LAMINA S.R.L.

Via Santellone, 29/A • 25080 Molinetto di Mazzano (BS) • Italy
 Tel. +39 (0) 30 21 20 448 • Fax +39 (0) 26 20 813
 Capitale Sociale € 46.800,00 Interamente versato
 C.F. e Nr. Iscr. Registro Imprese 01685670174
 P.I. IT01685670174 • REA BS-262362
 PEC: dhlamina@pec.it • dhlamina@dhlamina.it • www.dhlamina.it